



# M Screen Deco™

3% & 5% Openness



3% Openness  
▼

00D137  
River Rock

00D237  
Hazelnut

00D012  
Parchment

00D212  
Tumbleweed

00D112  
Naturelle

00D226  
Harvest



00D249  
Flagstone  
3% Openness

00D249  
Flagstone  
5% Openness

# M Screen Deco™

## 3% & 5% Openness

### Specifications 3% 5%

Item Number	008553	008555
Product Category	Decorative	
Openness Factor	3%	5%
% Fiberglass / % Vinyl	36% Fiberglass / 64% Vinyl	
UV Blockage / approx.	97%	95%
Fabric Style	Rib Weave	

### Dimensions

Standard Packaging	Rolls 30 ly (27 lm)	
Width	98" (250 cm)	
Weight	3%	12.21 oz / yd <sup>2</sup> (414 g / m <sup>2</sup> ) ± 5%
	5%	11.3 oz / yd <sup>2</sup> (385 g / m <sup>2</sup> ) ± 5%
Thickness	3%	0.023" (0.58 mm) ± 5%
	5%	0.020" (0.52 mm) ± 5%

### Fenestration

#### Fabric Properties

#### Fabric & Glass

COLOR	NUMBER	OPENNESS	Thermal Total Solar				Optical		Commercial SHGC % Improvement		Residential SHGC	
			Rs%	As%	Ts%	RV%	Tv%	Interior	Exterior	Interior	Exterior	
Flagstone	00D249	3%	23	71	6	23	5	24	84	0.54	0.10	
		5%	20	72	8	20	7	21	84	0.57	0.11	
River Rock	00D137	3%	33	60	7	35	6	29	84	0.49	0.10	
		5%	33	57	10	35	9	29	82	0.50	0.12	
Hazelnut	00D237	3%	13	83	4	12	4	16	84	0.59	0.10	
		5%	14	79	7	13	7	16	84	0.60	0.11	
Parchment	00D012	3%	64	20	16	67	12	50	82	0.33	0.14	
		5%	63	21	16	66	12	47	82	0.34	0.14	
Tumbleweed	00D212	3%	30	62	8	30	6	26	84	0.51	0.11	
		5%	29	61	10	29	8	24	84	0.53	0.12	
Naturelle	00D112	3%	54	33	13	57	9	42	82	0.38	0.13	
		5%	52	33	15	54	11	39	82	0.40	0.14	
Harvest	00D226	3%	15	79	6	14	5	18	84	0.58	0.11	
		5%	16	76	8	15	6	18	84	0.59	0.12	

### Cleaning

Remove dust with vacuum cleaner or compressed air. Do not scrub. Do not use solvents or any abrasive substance which might damage the coating of the fabric. Clean with a sponge or a soft brush dipped in soapy water using mild detergent. Rinse with clean water. Leave the blind down until completely dry. You can also very gently rub the fabric with a clean white pencil eraser to remove small stains.

The fabric performance tests were conducted in accordance with ASTM E891 & ASTM E903-96: Total Solar Transmittance (Ts), Total Solar Reflectance (Rs), Total Solar Absorptance (As), Visible Reflectance (Rv), and Visible Transmission (Tv). Glass performance tests for Solar Heat Gain Coefficient (SHGC) were conducted using the Lawrence Berkeley National Laboratory Window 7.3 NFRC certified software. SHGC % improvement for commercial applications is based on a standard commercial glass makeup of Double Glazing 6 mm / 1/2" air / 6 mm with low E on surface #2. SHGC for residential applications is based on a default residential glass makeup of 3 mm clear glass / 1/2" air / 3 mm clear glass. Results for SHGC were obtained using the center of glass. Acoustical performance was tested in accordance with ASTM C423-09a: NRC is Noise Reduction Coefficient, SAA is Sound Absorption Average. The Complex Glazing Report is available to fully evaluate glazing and window shade performance. For up-to-date test results, performance specifications and larger samples, contact the Mermet Technical Department at: [www.mermetusa.com](http://www.mermetusa.com).

### Classifications

Fire	NFPA 701-10 TM#1, California U.S. Title 19 CAN/ULC-S109-03 Small & Large Flame Test
Bacterial & Fungal Resistance	ASTM E2180, ASTM G21
Environmental Benefits	RoHS - Lead Free
Acoustical Performance	3% NRC: 0.35, SAA: 0.33 5% NRC: 0.10, SAA: 0.12



For additional information, questions, or to request fabric samples, please contact your Draper sales representative or visit <https://request.draperinc.com>

